

Rezeptliste und Mischungsberechnungen

4-Kammer-Anlage MA 15-4

	Bezeichnung	Körnung	S1 - 0-2	S2 - 0-2	S3 - 8-16	S4 2-8 / 2-5	Zement	VZ	Gewicht
		mm	kg	kg	kg	kg	kg		total in kg
Rez 1	BM 0-8 / 20-25	0-8	600	600		600	300		2180
Rez 2	BM 0-8 / 20-25	0-8	600	600		600	300	X	2180
Rez 3	BM 0-8 / 25-30	0-8	600	600		600	330		2215
Rez 4	BM 0-8 / 25-30	0-8	600	600		600	330	X	2215
Rez 5	BM 0-16 / 12-15	0-16	450	450	600	300	250		2120
Rez 6	BM 0-16 / 12-15	0-16	450	450	600	300	250	X	2120
Rez 7	BM 0-16 / 20-25	0-16	450	450	600	300	270		2145
Rez 8	BM 0-16 / 20-25	0-16	450	450	600	300	270	X	2145
Rez 9	BM 0-16 / 25-30	0-16	450	450	600	300	300		2180
Rez 10	BM 0-16 / 25-30	0-16	450	450	600	300	300	X	2180
Rez 11	BM 0-2 / 20-25	0-2	900	900			330		2205
Rez 12	BM 0-2 / 20-25	0-2	900	900			330	X	2205
Rez 13	Monokorn 2-8	2-8				1600	340		2235
Rez 14	Monokorn 2-8	2-8				1600	340	X	2235
Rez 15	Monokorn 8-16	8-16			1600		340		2205
Rez 16	Monokorn 8-16	8-16			1600		340	X	2205

2-Kammer-Anlage MA 15-2

	Bezeichnung	Körnung	S1 - 0-8	S2 - 8-16			Zement	VZ	Gewicht
		mm	kg	kg			kg		total in kg
Rez 1	BM 0-8 / 20-25	0-8	1800				300		2180
Rez 2	BM 0-8 / 20-25	0-8	1800				300	X	2180
Rez 3	BM 0-8 / 25-30	0-8	1800				330		2215
Rez 4	BM 0-8 / 25-30	0-8	1800				330	X	2215
Rez 5	BM 0-16 / 12-15	0-16	1200	600			250		2120
Rez 6	BM 0-16 / 12-15	0-16	1200	600			250	X	2120
Rez 7	BM 0-16 / 20-25	0-16	1200	600			270		2145
Rez 8	BM 0-16 / 20-25	0-16	1200	600			270	X	2145
Rez 9	BM 0-16 / 25-30	0-16	1200	600			300		2180
Rez 10	BM 0-16 / 25-30	0-16	1200	600			300	X	2180